



18 - 20 July 2018
International Congress

water, waste
and energy management
Madrid / Spain

ABSTRACTS

B O O K

ISBN 978-84-09-03238-9



SciKnowledgeTM
European Education Scientific Conferences

Activated carbons prepared from a compost obtained in mechanical biological treatment plants for municipal solid waste processing

J.L. Diaz de Tuesta ^(1,2), C.M. Masso ^(1,3), Juliana M.T. de A. Pietrobelli ⁽³⁾,
Adrián M.T. Silva ⁽²⁾, Joaquim L. Faria ⁽²⁾, Helder T. Gomes ^(1,2)

⁽¹⁾ *Centro de Investigação de Montanha (CIMO), Instituto Politécnico de Bragança, 5300-253 Bragança, Portugal.*

Phone number: +351273303110, E-mail: htgomes@ipb.pt

⁽²⁾ *Laboratory of Separation and Reaction Engineering - Laboratory of Catalysis and Materials (LSRE-LCM), Faculdade de Engenharia, Universidade do Porto, 4200-465 Porto, Portugal.*

⁽³⁾ *Universidade Tecnológica Federal do Paraná, Campus Ponta Grossa. Av. Monteiro Lobato, S/N. Km 04. Jardim Carvalho 84016 210 - Ponta Grossa, PR – Brasil.*

1. Introduction - Activated carbons (ACs) obtained from different organic wastes have been reported in several works, aiming the valorisation of low-cost useful materials [1]. However, organic wastes typically contain inorganic substances, which can be leached away from the prepared ACs when employed in oxidative aqueous conditions. The current study proposes different strategies to produce ACs from a compost obtained (in excess) during the treatment of the organic fraction of municipal solid waste by anaerobic digestion and maturation in waste management sites.

2. Experimental - The ACs were prepared by H₂SO₄ chemical treatment of the compost and carbonization at 800 °C, adapting the procedure reported elsewhere [1] and exploring three different approaches to avoid iron leaching: (i) preparation of AC from the organic waste obtained as the result of dissolving the compost in cyclohexane at 50 °C and further separation by evaporation; (ii) preparation of AC from a mixture of compost-glycerol, aiming to encapsulate the inorganic content; and (iii) washing the AC prepared directly from the compost with 0.5 M H₂O₂ at 80 °C. These samples were tested in the catalytic decomposition of H₂O₂ (0.5 M, pH 3 and AC load 2.5 g/L).

3. Results and Discussion - The extraction of organic content from the compost when using cyclohexane (approach i) was not enough to produce a suitable AC. In contrast, samples were successfully prepared by (ii) and (iii), showing catalytic activity in the decomposition of H₂O₂ (conversions of H₂O₂ higher than 50 % at room temperature after 2 h), the leaching of iron being not detected for the sample obtained by (iii).

4. Conclusions – The valorisation of a compost to produce an active and stable AC catalyst is possible by activation with H₂SO₄, carbonization at 800 °C and washing with a H₂O₂ solution at 80 °C.

Acknowledgements - This work is a result of projects: VALORCOMP, funded by FEDER through Programme INTERREG V A Spain - Portugal (POCTEP) 2014–2020; “AIProcMat@N2020 - Advanced Industrial Processes and Materials for a Sustainable Northern Region of Portugal 2020”, with reference NORTE-01-0145-FEDER-000006 and supported by NORTE 2020 under the Portugal 2020 Partnership Agreement, through FEDER; and POCI-01-0145-FEDER-006984 – Associate Laboratory LSRE-LCM funded by FEDER through COMPETE2020 - POCI – and by national funds through FCT.

5. References

[1] R.S. Ribeiro, A.M.T. Silva, M.T. Pinho, J.L. Figueiredo, J.L. Faria, H.T. Gomes. *Catal. Today* 240 (2015) p. 61.